


BergaClassic Preprint

by Stora Enso



storaenso

BergaClassic Preprint is a woodfree uncoated paper for offset printing presses and subsequent personalization in laser printers.

- Designed for multiple needs: from constat forms to A4 letterheads
- Good runnability in converting, laser, inkjet, plotter, automatic inserting
- Good printability in 3/4 colour printing

PRODUCER

Nymölla Mill

TYPICAL END USES

Letterheads
Direct mail
Technical manuals
Statements
Invoices

CONVERTING

Reel-to-A4
Reel-to-reel
Reel-to-fanfold

PRINTING METHODS

UV-Offset
Cold Set Web Offset
Plain Paper Copiers
Inkjet (dye)
HSWO

L* a* b* target values

ISO 5631-3
(D50/2°)

L*	a*	b*	Fluorescence (ISO 12647-2)
92	2.8	-10.7	High

ICC-PROFILE

Download: [Technical Resource Centre](#)

POST PRINTING PROCESS

Laser
Automatic inserting
Plotter

TECHNICAL SPECIFICATIONS (target values, afetr production)

Substance		g/m ²	70	75	80	90	100	115
Brightness	ISO 2470-2 (D65/10°)	%	109	109	109	109	109	109
CIE Whiteness	ISO 11475 (D65/10°)	%	163	163	163	163	163	163
Opacity	ISO 2471	%	91	92	94	95	96	97
Bulk	ISO 534	cm ³ /g	1.30	1.30	1.30	1.30	1.30	1.30
Roughness	Bendtsen, ISO 8791-2	ml/min	270	270	270	270	270	270

REEL SPECIFICATIONS

Cores: 70, 76 & 152 mm
Width: min. 210 mm, max. 2600 mm
Diameters: 1000 & 1200 mm

ENVIRONMENT

Renewable fibre
Recyclable paper
Recyclable packaging materials

CERTIFICATES Nymölla

Quality ISO 9001
Environment ISO 14001
Health & Safety ISO 45001
Energy ISO 50001
EU Ecolabel SE/011/001
Nordic Ecolabel No: 3044 0044
For more information:
www.storaenso.com/paper-sustainability

STORAGE AND HANDLING

- Store the paper in a humidity and temperature controlled area at 50% relative humidity and room temperature between 19°C and 23°C.
- If the paper is stored in non-air conditioned warehouse, it is absolutely necessary to allow a stabilisation period in the print room.
- Open the protective wrapping at the moment of use.